

# ARDEX X10

# Flexible Non Slump Wall and Floor Tile Adhesive

Flexible – achieves S1 classification

Non slump – ideal for large format and heavy tiles

Extended open time

Good workability with low sand content

Ideal for all tile types including fully vitrified, porcelain and mosaics

Suitable for wall and floor tiling

For internal and external use

Low VOC content - meets Green Building Council of Australia Green Star IEQ-13 requirements

ARDEX Australia Pty Ltd 20 Powers Road Seven Hills NSW 2147 Tel: (02) 9851 9199

Fax: (02) 9851 9199

Email: techinfo@ardexaustralia.com

Internet: www.ardex.com

ARDEX New Zealand Ltd 32 Lane St, Woolston Christchurch, New Zealand

Tel: (03) 384 3029 Fax: (03) 384 9779

Email: techinfo@ardexaustralia.com

Internet: www.ardex.com

# ARDEX X10

## Flexible Non Slump Wall and Floor Tile Adhesive

ARDEX X10 is a white polymer fortified cement-based wall and floor tile adhesive that has been specially formulated with mastic type properties. ARDEX X10 has an extended open time, is non slump and flexible. Mix with water to achieve a mortar suitable for internal and external use in residential, commercial and industrial applications. ARDEX X10 meets the Green Building Council of Australia Green Star IEQ-13 requirements for Ceramic Tile Adhesives.

#### FOR FIXING (TILE TYPES)

Fully vitrified and ceramic tiles, porcelain, natural stones (excluding moisture sensitive) and mosaics.

#### TO (SUBSTRATES)

Concrete, renders, screeds Fibre-cement sheet, plasterboard ARDEX liquid applied undertile waterproofing membranes. Existing ceramic tiles

#### SUBSTRATE PREPARATION

The surface being adhered to must be clean, firm and free of dust, dirt, oil, grease, curing compounds, release agents and other barrier materials, as well as being strong enough to support the weight of the tiles being fixed. Ensure surfaces are dry before tiling, with no residue or permanent damp.

Ensure that the substrate's required drying time, as given in the relevant part of AS 3958, is allowed to elapse prior to fixing the tiles. Prime porous substrates with ARDEX Multiprime.

#### Concrete

This includes precast, in-situ and wood floated concrete. As concrete exhibits drying shrinkage, allow to cure for at least 4 weeks prior to tiling. Any surface laitance, concrete sealers, curing compounds, and other materials should be removed from the surface prior to tiling. Steel trowel finished concrete should be roughened mechanically to remove laitance and provide a good key for tiling. The surface should be true and level and pitched to drains where required. The concrete should have adequate surface profile (e.g. broom finish) to provide a mechanical key. Smooth surfaces and/or dense concrete greater than 35MPa must be mechanically prepared prior

### Cement Render/Screeds

New renders and screeds should be finished with a wood float to the required surface regularity. Screeds should be pitched to drains where required. Allow at least 7 days to cure prior to

## Plasterboard/Medium Density Fibre-Cement

Tiles can be fixed directly provided these boards are firmly and rigidly fixed in accordance with manufacturer's instructions to adequately support the tile bed. Priming is recommended for fibre-cement sheet but is not usually necessary for plasterboard except when jointing compound

#### **Compressed Fibre-Cement Sheet Internal Applications**

These sheets must be fixed strictly in accordance with manufacturer's instructions and be deemed suitable for the application by the manufacturer. Tiling over compressed fibre-cement sheet for external flooring applications should be carried out as per sheet manufacturer's recommendations and Australian Standard AS 3958.

## ARDEX Liquid Applied Undertile Waterproofing

ARDEX undertile waterproofing must be applied according to instructions and thoroughly dry prior to tiling.

#### **Existing Ceramic Tiles (Internal Only)**

These include sound, clean, glazed and unglazed tiles. Existing tiles must be firm and stable. Roughen the surface by mechanical means, clean off contamination and dust before tiling. Ensure that at least 80% of the glaze is removed. Tiling over existing tiles is not recommended in immersed applications.

#### MIXING

ARDEX X10 powder is added to clean water in a clean container whilst stirring vigorously and mixed thoroughly to give a lump free easily worked mortar of a thick creamy consistency. Allow to stand for 5 minutes. Restir the mixture thoroughly and the adhesive is ready for use. A 20kg bag of ARDEX X10 requires approximately 5.5 litres of water. Do not add additional water.

The consistency of the adhesive can be slightly adjusted to suit site conditions and size, weight and type of tiles to be fixed. Do not apply at temperatures below 5°C. The pot life of the mixed mortar is approximately 3 hours at 23°C and 50% relative humidity.

#### **FIXING TECHNIQUE**

Before fixing ensure the substrate has been prepared and the tiles are free from dust. Tiles should be fixed in accordance with Australian Standard AS 3958.

Substrate surface, type and size of the tiles will determine the selection of the trowel. As a general guide use a 6 x 6 x 6mm notch trowel for walls and 10 x 10 x 10mm notch trowel for floor tiling. ARDEX X10 can be applied at a bed thickness greater than 3mm or less than 10mm.

The tiles must be pressed firmly into the freshly combed mortar bed to ensure good contact with the mortar. Slide the tile at right angles to the notch pattern to ensure 100% coverage on the back of the tile. Tiles with ribbed or keyed back profiles should also be buttered to ensure complete coverage. Lift a tile from time to time to check that there are no voids beneath the tile. Do not spot fix. Any surplus adhesive must be removed from the surface of the tile and joints, before the adhesive sets.

ARDEX X10 has an open time of 30 minutes and an adjustment time of 20 minutes. Please be aware of site conditions when considering these times and only spread enough adhesive so that the tiles can be fixed while the mortar is still wet. All tools should be cleaned with water immediately

#### **MOVEMENT JOINTS**

Movement joints must be in accordance with Australian Standard AS 3958.

Grouting can proceed once the tile bed has hardened sufficiently so that tiles will not be dislodged. Grouting and traffic may be allowed after approximately 24 hours at 23°C and 50% relative humidity. Allow longer for dense tiles/ substrates, humid climates and low temperatures.

The tile joints should be grouted with the appropriate ARDEX grout.

#### COVERAGE

20kg of ARDEX X10 is sufficient for approximately 8m<sup>2</sup> on walls, using a 6 x 6 x 6mm notched trowel and 6m<sup>2</sup> on floors using a 10 x 10 x 10mm notched trowel. The coverage will vary depending on substrate condition, tile type and application technique.

## **PACKAGING**

ARDEX X10 is packed in polylined paper sacks net weight 20kg.

ARDEX X10 has a shelf life of not less than 12 months when stored in the original unopened packaging, in a dry place at 23°C and 50% relative humidity.

## Pay attention to the following:

Do not use ARDEX X10 in continuous immersion applications e.g. swimming pools, tanks, etc. ARDEX provides other systems.

Do not use over metal or similar substrates.

ARDEX X10 should not be used over substrates subject to shrinkage and other movement e.g. timber, ARDEX provides other systems.

For setting of moisture sensitive natural stones, please refer to products in the ARDEX Natural Stone System.

#### SAFETY PRECAUTIONS

This product is considered non hazardous in normal usage. The presence of cement in the product gives an alkaline mortar which may cause some irritation if prolonged contact with skin takes

Avoid contact with skin and eyes; in case of contact with the eyes, rinse immediately with plenty of water and seek medical advice; wear suitable gloves and eye protection and keep the product out of the reach of children. Avoid generation of airborne dust during mixing. If swallowed do not induce vomiting, give a glass of water and contact a doctor.

For further material safety data, consult the latest Material Safety Data Sheet.

#### **TECHNICAL DATA**

White Powder Colour:

Mixing Ratio: 1 vol water:3 vol powder,

approximately 5.5 litres water per 20kg powder

Application Properties at 23°C and 50% RH

30 minutes Open Time: Adjustment Time: 20 minutes Grouting Time: 24 hours 3 hours Pot life: None Sagging:

#### Mechanical Properties (AS 4992) Tensile Adhesion Strength after

1.0 – 1.5 MPa 28 days dry: Water Immersion: 1.0 - 1.5 MPa 1.0 - 1.5 MPa Heat: Freeze Thaw: 0.5 - 1.0 MPa C1 TE S1 Classification:

## ARDEX Australia Pty Ltd

Ph (02) 9851 9100 Fax (02) 9838 7970 NSW Ph (07) 3817 6000 Fax (07) 3881 3188 QLD VIC/TAS Ph (03) 9308 9255 Fax (03) 9308 9332 Ph (08) 8268 2511 Fax (08) 8345 3207 SA Ph (08) 9256 8600 Fax (08) 9455 1227

#### **ARDEX New Zealand Ltd**

Auckland Ph (09) 2967 690 Fax (09) 2967 689 Wellington Ph (04) 5685 949 Fax (04) 5686 376 Christchurch Ph (03) 3843 029 Fax (03) 3849 779

#### Technical Services Toll Free: 1800 224 070 DISCLAIMER

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standard, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Pty Ltd 2009.

All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.

March 2009