



ARDEX Abaflex

Premium Polymer Modified Flexible Tile Adhesive

Now achieves C2 classification

High performance - Use in critical applications e.g. shopping centres

Use over early age concrete/screeds and render

Flexible – achieves S1 classification

Non-slump – achieves T rating

Suitable for floor and wall tiling

Excellent workability

ARDEX Abaflex is ideal for fixing a range of tile types including ceramic, fully vitrified, porcelain, natural stone, terrazzo and mosaics

For internal and external use

Low VOC content - meets Green Building Council of Australia Green Star IEQ-13 requirements



ARDEX Australia Pty Ltd
20 Powers Road
Seven Hills NSW 2147
Tel: (02) 9851 9199
Fax: (02) 9674 5621
Email: techinfo@ardexaustralia.com
Internet: www.ardex.com

ARDEX New Zealand Ltd
32 Lane St, Woolston
Christchurch, New Zealand
Tel: (03) 384 3029
Fax: (03) 384 9779
Email: techinfo@ardexaustralia.com
Internet: www.ardex.com

ARDEX Abaflex

Premium Polymer Modified Flexible Tile Adhesive

DESCRIPTION

ARDEX Abaflex is a premium grade, cement-based wall and floor tile adhesive, which has excellent flexibility and is dry enough to be grouted after 8 hours. It has superior workability and is ideal for fixing fully vitrified, porcelain, mosaics and non-moisture sensitive natural stone tiles. ARDEX Abaflex is suitable for use in both internal and external applications and is especially suited to high performance situations with heavy pedestrian traffic e.g. shopping centres. ARDEX Abaflex accommodates shrinkage movement associated with early age concrete and screeds, it can be used over concrete that is at least 7 days old and screeds and renders after 16 hours. It is flexible enough to withstand crack opening of up to 0.9mm. ARDEX Abaflex meets the Green Building Council of Australia Green Star IEQ-13 requirements for Ceramic Tile Adhesives.

FOR FIXING (TILE TYPES)

Fully vitrified and ceramic tiles, porcelain, natural stones (excluding moisture sensitive), glass and porcelain mosaics.

TO (SUBSTRATES)

Concrete, renders, screeds
ARDEX liquid applied undertile waterproofing membranes
Medium density fibre-cement sheets, compressed fibre-cement sheet, plasterboard
Existing ceramic and vinyl tiles
Autoclaved aerated concrete (AAC)

SUBSTRATE PREPARATION

The surface being adhered to must be clean, firm and free of dust, dirt, oil, grease, curing compounds, release agents and other barrier materials, as well as being strong enough to support the weight of the tiles being fixed. Ensure surfaces are dry before tiling, with no residue or permanent damp.

Concrete (including early age concrete)

Early age concrete must be a minimum of 7 days old and no less than 20 MPa. Protect the slab from moisture escape directly after pouring concrete (i.e. cover with plastic sheet or similar system). Prior to tiling, remove any concrete sealers or curing compounds from the surface, e.g. chlorinated rubber, resin, wax sealers. Steel trowel finished concrete should be roughened mechanically to remove laitance and provide a good key for tiling. The surface should be true and level and pitched to drains where required. Smooth surfaces and/or dense concrete greater than 35 MPa must be mechanically roughened prior to tiling.

Cement Render/Screeds

New renders and screeds, consisting of one part cement to three or four parts sand, should be finished with a wood float to the required surface regularity to establish a mechanical key. It should be no less than 10mm in thickness. Curing time is a minimum of 16 hours before tiling can commence. Screeds should be pitched to drains where required.

Plasterboard/Medium Density Fibre-Cement Sheet

Provided that these boards are firmly and rigidly fixed in accordance with the manufacturers instructions to adequately support the tile bed, tiles can be fixed directly. Please ensure the surface is completely clean. Priming with ARDEX Multiprime is recommended over fibre-cement sheets, followed by taping of sheet joints with PVC ducting tape. Priming is not usually necessary for plasterboard except when a jointing compound is used, the compound should then be primed with ARDEX Multiprime.

Painted Surfaces

Thoroughly remove painted surfaces mechanically, do not use paint stripper or solvents. Allow surface to dry after cleaning.

Existing Vinyl Tiles

Ensure vinyl tiles are well bonded to the substrate.

Remove wax, polish and any loose tiles. Roughen with coarse sand paper then clean the surface with warm water.

Existing Ceramic Tiles (Internal Only)

These include sound, clean, glazed and unglazed tiles. Existing tiles must be firm and stable. Roughen the surface by mechanical means, clean off contamination and dust before tiling. Ensure that at least 80% of the glaze is removed.

Compressed Fibre-Cement Sheet

These sheets must be fixed strictly in accordance with manufacturer's instructions and be deemed suitable for the application by the manufacturer. Tiling over compressed fibre-cement sheets for external flooring applications should be carried out as per sheet manufacturer's recommendations and Australian Standard AS 3958.

Autoclaved Aerated Concrete (AAC)

Remove loose particles from surface and apply two coats of ARDEX Multiprime before tiling.

MIXING

ARDEX Abaflex powder is added to clean water in a clean container whilst stirring vigorously and mixed thoroughly to give a lump free easily worked mortar of a thick creamy consistency. Allow to stand for 5 minutes. Restir the mixture thoroughly and the adhesive is ready for use. A 20kg bag of ARDEX Abaflex requires approximately 4 litres of water. Do not add additional water. The consistency of the adhesive can be adjusted to suit site conditions and size, weight and type of tiles to be fixed. Do not apply at temperatures below 5°C. The pot life of the mixed mortar is approximately 2 hours at 23°C and 50% relative humidity.

FIXING TECHNIQUE

Before fixing ensure the substrate has been prepared and the tiles are free from dust. Tiles should be fixed in accordance with AS 3958. Substrate surface, type and size of the tiles will determine the selection of the trowel. As a general guide use a 6 x 6 x 6mm notched trowel for walls and 10 x 10 x 10mm notched trowel for floor tiling. ARDEX Abaflex can be applied at a bed thickness greater than 1.5mm or less than 10mm. The tiles must be pressed firmly into the freshly combed mortar bed to ensure good contact with the mortar. Slide the tile at right angles to the notch pattern to ensure 100% coverage on the back of the tile. Tiles with ribbed or keyed back profiles should also be buttered to ensure complete coverage. Lift a tile from time to time to check that there are no voids beneath the tile. Do not spot fix. Any surplus adhesive must be removed from the surface of the tile and joints, before the adhesive sets. ARDEX Abaflex has an open time of 30 minutes and an adjustment time of 45 minutes. Please be aware of site conditions when considering these times and only spread enough adhesive so that the tiles can be fixed while the mortar is still wet. All tools should be cleaned with water immediately after use.

MOVEMENT JOINTS

Movement joints must be in accordance with Australian Standard AS 3958.

GROUTING

Grouting can proceed once the tile bed has hardened sufficiently so that tiles will not be dislodged. Light foot traffic may be allowed after approximately 8 hours and full traffic after approximately 24 hours at 23°C and 50% relative humidity. Allow longer for dense tiles/substrates, humid climates and low temperatures. The tile joints should be grouted with the appropriate ARDEX grout. When grouting over early age concrete, mix the grout with ARDEX Grout Booster as per grout packaging instructions.

COVERAGE

20kg of ARDEX Abaflex is sufficient for approximately 7m² on walls, using a 6 x 6 x 6mm notched trowel and 5m² on floors using a 10 x 10 x 10mm notched trowel. The coverage will vary

depending on substrate condition, tile type and application technique.

PACKAGING

ARDEX Abaflex is packed in polylined paper sacks – net weight 20kg.

SHELF LIFE

ARDEX Abaflex has a shelf life of not less than 12 months when stored in the original unopened packaging, in a dry place at 23°C and 50% relative humidity.

Pay attention to the following:

When setting tiles on shrinking substrates, limit the size of the area and ensure adequate movement joints are incorporated.

For setting of moisture sensitive natural stones, please refer to products in the ARDEX Natural Stone System.

ARDEX Abaflex is not suitable for use over timber floors, non-absorbent substrates e.g. metal, or continuous immersion applications, such as swimming pools and water tanks. ARDEX provides other systems.

SAFETY PRECAUTIONS

This product is considered non hazardous in normal usage. The presence of cement in the product gives an alkaline mortar which may cause some irritation if prolonged contact with skin takes place.

Avoid contact with skin and eyes; in case of contact with the eyes, rinse immediately with plenty of water and seek medical advice; wear suitable gloves and eye protection and keep the product out of the reach of children. Avoid generation of airborne dust during mixing. If swallowed do not induce vomiting, give a glass of water and contact a doctor.

For further material safety data, consult the latest Material Safety Data Sheet.

TECHNICAL DATA

Colour: Off White Powder
Mixing Ratio: Approx
4L water/20kg powder

Application Properties at 23°C and 50% RH

Open Time: 30 minutes
Adjustment Time: 45 minutes
Grouting Time: 8 hours
Pot Life: 2 hours
Underfloor Heating: Yes

Mechanical Properties (AS 4992)

Tensile Adhesion Strength: 1.0 MPa
28 days dry: 1.0 MPa
Water immersion: 1.0 MPa
Heat: 1.0 MPa
Freeze Thaw: C2 T S1
Classification:

ARDEX Australia Pty Ltd

NSW Ph (02) 9851 9100 Fax (02) 9838 7970
QLD Ph (07) 3817 6000 Fax (07) 3881 3188
VIC/TAS Ph (03) 9308 9255 Fax (03) 9308 9332
SA Ph (08) 8268 2511 Fax (08) 8345 3207
WA Ph (08) 9256 8600 Fax (08) 9455 1227

ARDEX New Zealand Ltd

Auckland Ph (09) 2967 690 Fax (09) 2967 689
Wellington Ph (04) 5685 949 Fax (04) 5686 376
Christchurch Ph (03) 3843 029 Fax (03) 3849 779

Technical Services Toll Free: 1800 224 070

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standard, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them. © ARDEX Australia Pty Ltd 2008.

All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.